

AUSSIÈRES TRESSÉS · **MOORING ROPES** · ESTACHAS



NYLON

REF	CIRC. POUCE CIRC. INCH CIRC. PULGADAS	METRAGE RUNNAGE METRAJE		CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA	
		Kg/100 m	lb/100 ft	kfg	lb
2NY40T	5"	99.0	66.5	30.000	66.080
2NY44T	5 1/2"	120.0	81.0	35.800	78.850
2NY48T	6"	142.0	95.0	42.000	92.510
2NY52T	6 1/2"	166.0	112.0	48.800	107.490
2NY56T	7"	193.0	130.0	56.000	123.350
2NY60T	7 1/2"	221.0	148.0	63.800	140.500
2NY64T	8"	252.0	169.0	72.000	158.600
2NY72T	9"	319.0	214.0	90.000	198.200
2NY80T	10"	394.0	264.0	110.000	242.300

POLYSTEEL

REF	CIRC. POUCE CIRC. INCH CIRC. PULGADAS	METRAGE RUNNAGE METRAJE		CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA	
		Kg/100m	lb/100ft	kfg	lb
2PS40T	5"	72.0	48.3	26.860	59.160
2PS44T	5 1/2"	88.0	59.1	31.780	70.000
2PS48T	6"	104.0	69.8	37.180	81.890
2PS52T	6 1/2"	122.0	82.0	43.195	95.140
2PS56T	7"	142.0	95.3	49.380	108.760
2PS60T	7 1/2"	163.0	109.5	56.680	124.840
2PS64T	8"	185.0	124.0	64.140	141.270
2PS68T	8 1/2"	209.0	140.7	72.062	158.720
2PS72T	9"	234.0	157.0	80.225	176.700

**NABERAN SAREAK S.L.**

Mutrikuko Industrialdea 15  
20830 Mutriku - Gipuzkoa  
+34 943 195 122 | naberan@naberan.com

**NABERAN FRANCE SARL**

Avenue de la République  
ZA Poriguenor | 29730 Le Guilvinec (France)  
+33 298 582 739 | david@naberan.com