


CORDES TRESSÉES · BRAIDED ROPES · CUERDAS TRENZADAS



NYLON

REF	POIDS WEIGHT PESO 100 mts	CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA
2NY06TATB	2.25	750
2NY08TATB	4.00	1.350
2NY10TATB	6.20	2.080
2NY12TATB	8.90	3.000
2NY14TATB	12.20	4.100
2NY16TATB	15.80	5.300
2NY18TATB	20.00	6.700
2NY20TATB	24.50	8.300
2NY22TATB	30.00	10.000
2NY24TATB	35.50	12.000
2NY26TATB	42.00	14.000
2NY28TATB	48.50	15.800
2NY30TATB	55.50	17.800
2NY32TATB	63.00	20.000

POLIESTER

REF	POIDS WEIGHT PESO 100 mts	CHARGE RUPTURE BREAKING STRENGTH CARGA ROTURA
2PT06TATB	12.70	565
2PT08TATB	4.80	1.020
2PT10TATB	7.60	1.590
2PT12TATB	11.00	2.275
2PT14TATB	14.80	3.180
2PT16TATB	19.50	4.060
2PT18TATB	24.50	5.080
2PT20TATB	30.50	6.355
2PT22TATB	36.70	7.620
2PT24TATB	43.70	9.140
2PT26TATB	51.20	10.710
2PT28TATB	59.40	12.240
2PT30TATB	68.20	13.670
2PT32TATB	77.80	15.700

NABERAN SAREAK S.L.

Mutrikuko Industrialdea 15
20830 Mutriku - Gipuzkoa
+34 943 195 122 | naberan@naberan.com

NABERAN FRANCE SARL

Avenue de la République
ZA Poriguenor | 29730 Le Guilvinec (France)
+33 298 582 739 | david@naberan.com